

Material: AFNOR NF 35 NCD 16

Standard Specification for Mild Steel Alloys Bar, Wire and Rod

Group: Ferrous Mild Steel Alloys

Sub Group: AFNOR NF 35 NCD 16 Mild Steel Alloys Bar, Wire and Rod

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Bar, Wire and Rod

Chemical Composition			Heat Treatment	
Carbon	C %	0.320 - 0.390	As Raw or Annealing or Normalizing or Hardening and Tempering	
Silicon	Si %	0.100 - 0.400		
Manganese	Mn %	0.300 - 0.600		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.025 max.		
Chromium	Cr %	1.600 - 2.000		
Molybdenum	Mo %	0.250 - 0.450		
Nickel	Ni %	3.600 - 4.100		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	1000 - 1380
-	-	-	Yield Strength in Mpa	800 min.
-	-	-	Elongation in %	8 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	269 max.
-	-	-	Impact in Joule	50 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
35NiCrMo16	EN	European Union	Bar and Rod
1.6773	EN	European Union	Bar and Rod
835 M 30	BS	British	Bar and Rod
SFNCM 1030 R	JIS	Japan	Forging
SFNCM 830 R	JIS	Japan	Forging
SFNCM 880 R	JIS	Japan	Forging
SFNCM 930 R	JIS	Japan	Forging

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com