

# Material: AFNOR NF CuZn40Mn1Pb1FeSn

## Standard Specification for Copper and Copper Alloy Rod

**Group:** Non Ferrous Copper Alloys

**Sub Group:** AFNOR NF CuZn40Mn1Pb1FeSn Copper and Copper Alloy Rod

**Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries**

**Grade Belongs to the Industry:** Rod

Chemical Composition		
Aluminium	Al %	0.100 max.
Iron	Fe %	0.200 - 1.200
Manganese	Mn %	0.800 - 1.800
Nickel	Ni %	0.300 max.
Lead	Pb %	0.800 - 1.600
Tin	Sn %	0.200 - 1.000
Other	Ot %	0.300 max.
Copper	Cu %	56.500 - 58.500
Zinc	Zn %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment	
As Raw or Solution Heat Treated	

Mechanical Properties	
Tensile Strength in Mpa	440 min.
Yield Strength in Mpa	180 min.
Elongation in %	10 min.
Reduction of Area in %	-
Hardness in HV	110 - 150
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CuZn40Mn1Pb1FeSn	DIN	Germany	Rod
C37710	UNS	USA	Rod
CuZn40Mn1Pb1FeSn	NBN	Belgium	Rod
CW722R	NBN	Belgium	Rod
CuZn40Mn1Pb1FeSn	MSZ	Hungary	Rod
CW722R	MSZ	Hungary	Rod
CW722R	AFNOR NF	France	Rod

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)



+91-99090 45075



[info@icastllp.com](mailto:info@icastllp.com)



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India