

Material: AFNOR NF EN 1706 AC- 71000

Standard Specification for Aluminium and Aluminium Alloys - Casting

Group: Non-Ferrous Aluminium Alloy

Sub Group: AFNOR NF EN 1706 Aluminium and Aluminium Alloys - Casting

Application : Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Copper	Cu %	0.150 - 0.350	As-Cast or Aging	
Iron	Fe %	0.800 max.		
Magnesium	Mg %	0.400 - 0.700		
Manganese	Mn %	0.400 max.		
Nickel	Ni %	0.050 max.		
Silicon	Si %	0.300 max.		
Titanium	Ti %	0.100 - 0.250		
Lead	Pb %	0.050 max.		
Tin	Sn %	0.050 max.		
Chromium	Cr %	0.150 - 0.600		
Zinc	Zn %	4.500 - 6.000	Mechanical Properties Tensile Strength in Mpa 190 - 210 Yield Strength in Mpa 120 - 130 Elongation in % 4 min. Reduction of Area in % - Hardness in HB 60 - 62 Impact in Joule -	
Other	Ot%	0.150 max.		
Aluminium	Al %	Balance		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN AC-71000	DIN	Germany	Casting
EN AC-71000	BS	British	Casting
EN AC-71000	UNI	Italy	Casting
Al Zn5Mg	ISO	International	Casting
EN AC-71000	UNE	Spain	Casting
EN AC-71000	SFS	Finland	Casting
EN AC-71000	BDS	Bulgaria	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and/or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com