

Material: AFNOR NF EN 1706 AC-21100

Standard Specification for Aluminium and Aluminium Alloys - Castings

Group: Non-Ferrous Aluminium Alloy

Sub Group: AFNOR NF EN 1706 Aluminium and Aluminium Alloys - Castings

Application : Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Copper	Cu %	4.500 - 5.200	As-Cast or Solution Annealing and Aging	
Iron	Fe %	0.190 max.		
Manganese	Mn %	0.550 max.		
Silicon	Si %	0.180 max.		
Titanium	Ti %	0.150 - 0.300		
Zinc	Zn %	0.070 max.		
Other	Ot%	0.100 max.		
Aluminium	Al %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 280 - 450 Yield Strength in Mpa 180 - 400 Elongation in % 3 - 20 Reduction of Area in % - Hardness in HB 85 - 145 Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN AC-21100	ASME	USA	Casting
EN AC-21100	DIN	Germany	Casting
EN AC-21100	UNE	Spain	Casting
EN AC-21100	SFS	Finland	Casting
EN AC-21100	MSZ	Hungary	Casting
Al Cu4Ti	ISO	International	Casting
EN AC-21100	BDS	Bulgaria	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India