

# Material: AFNOR NF EN 1706 AC-46400

## Standard Specification for Aluminium and Aluminium Alloys - Casting

**Group:** Non-Ferrous Aluminium Alloy

**Sub Group:** AFNOR NF EN 1706 Aluminium and Aluminium Alloys - Casting

**Application :** Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

**Belongs to the Industry:** Casting

Chemical Composition			Heat Treatment	
Copper	Cu %	0.800 - 1.300	As-Cast	
Iron	Fe %	0.800 max.		
Magnesium	Mg %	0.250 -0.650		
Manganese	Mn %	0.150 - 0.550		
Nickel	Ni %	0.200 max.		
Silicon	Si %	8.300 -9.700		
Lead	Pb %	0.100 max.		
Tin	Sn %	0.100 max.		
Titanium	Ti %	0.200 max.		
Zinc	Zn %	0.800 max.		
Other	Ot%	0.250 max.		
Aluminium	Al %	Balance		
-	-	-		
-	-	-		
-	-	-		

  

Mechanical Properties	
Tensile Strength in Mpa	135 - 275
Yield Strength in Mpa	90 - 235
Elongation in %	1 - 2
Reduction of Area in %	-
Hardness in HB	60 - 105
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN AC-46400	DIN	Germany	Casting
EN AC-46400	BS	British	Casting
EN AC-46400	ASME	USA	Casting
EN AC-46400	UNI	Italy	Casting
Al Si9Cu1Mg	ISO	International	Casting
EN AC-46400	UNE	Spain	Casting
EN AC-46400	SFS	Finland	Casting

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

**Customer Care:** +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)