

# Material: AFNOR NF EN 1982 CuSn10-C

## Standard Specification for Copper and Copper Alloys - Ingots and Castings

**Group:** Non-Ferrous Copper Alloy

**Sub Group:** AFNOR NF EN 1982 Copper and Copper Alloys - Ingots and Castings

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

**Belongs to the Industry:** Ingot and Casting

Chemical Composition		
Aluminium	Al %	0.010 max.
Iron	Fe %	0.200 max.
Manganese	Mn %	0.100 max.
Nickel	Ni %	2.000 max.
Phosphorus	P %	0.200 max.
Lead	Pb %	1.000 max.
Sulphur	S %	0.050 max.
Antimony	Sb %	0.200 max.
Silicon	Si %	0.020 max.
Tin	Sn %	9.000 - 11.000
Zinc	Zn %	0.500 max.
Cu + Ni	Cu%+Ni%	88.000 - 90.000
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Cast

Mechanical Properties	
Tensile Strength in Mpa	250 - 326
Yield Strength in Mpa	130 - 170
Elongation in %	10 - 45.6
Reduction of Area in %	-
Hardness in HB	70 - 80
Impact in Joule	48.4 - 49.9 @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CB480K	BS	British	Ingot and Casting
CC480K	ONORM	Australia	Ingot and Casting
CC480K	EN	European Union	Ingot and Casting
CC480K	DIN	Germany	Ingot and Casting
CC480K	BDS	Bulgaria	Ingot and Casting
CuSn10-C	UNE	Spain	Ingot and Casting
CuSn10-C	UNI	Italy	Ingot and Casting

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)



+91-99090 45075



[info@icastllp.com](mailto:info@icastllp.com)



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India