

Material: AFNOR NF EN 1982 CuSn3Zn8Pb5-B

Standard Specification for Copper and Copper Alloys - Ingots and Castings

Group: Non-Ferrous Copper Alloy

Sub Group: AFNOR NF EN 1982 Copper and Copper Alloys - Ingots and Castings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.010 max.	As-Cast	
Iron	Fe %	0.500 max.		
Nickel	Ni %	2.000 max.		
Phosphorus	P %	0.030 max.		
Lead	Pb %	3.500 - 5.800		
Sulphur	S %	0.080 max.		
Antimony	Sb %	0.250 max.		
Silicon	Si %	0.010 max.		
Tin	Sn %	2.200 - 3.500	Mechanical Properties Tensile Strength in Mpa 180 - 220 Yield Strength in Mpa 85 - 100 Elongation in % 12 - 15 Reduction of Area in % - Hardness in HB 60 - 70 Impact in Joule -	
Zinc	Zn %	7.500 - 10.000		
Cu + Ni	Cu%+Ni%	81.000 - 85.500		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CC490K	BS	British	Ingot and Casting
CB490K	DIN	Germany	Ingot and Casting
CuSn3Zn8Pb5-B	DIN	Germany	Ingot and Casting
CB490K	EN	European Union	Ingot and Casting
CuSn3Zn8Pb5-B	EN	European Union	Ingot and Casting
CB490K	AFNOR NF	France	Ingot and Casting
CB490K	UNI	Italy	Ingot and Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India