

Material: AFNOR NF EN 1982 CuZn37Al1-B

Standard Specification for Copper and Copper Alloys - Ingots and Castings

Group: Non-Ferrous Copper Alloy

Sub Group: AFNOR NF EN 1982 Copper and Copper Alloys - Ingots and Castings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.600 - 1.800	As-Cast	
Iron	Fe %	0.400 max.		
Manganese	Mn %	0.400 max.		
Nickel	Ni %	1.800 max.		
Phosphorus	P %	0.020 max.		
Lead	Pb %	0.400 max.		
Antimony	Sb %	0.050 max.		
Silicon	Si %	0.500 max.		
Tin	Sn %	0.400 max.		
Cu + Ni	Cu%+Ni%	60.000 - 63.000		
Zinc	Zn %	Balance	Mechanical Properties Tensile Strength in Mpa 450 min. Yield Strength in Mpa 170 min. Elongation in % 25 min. Reduction of Area in % - Hardness in HB 105 min. Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CC766S	BS	British	Ingot and Casting
CB766S	EN	European Union	Ingot and Casting
CB766S	BDS	Bulgaria	Ingot and Casting
CB766S	CSN	Czech Republic	Ingot and Casting
CB766S	DIN	Germany	Ingot and Casting
CuZn37Al1-B	UNE	Spain	Ingot and Casting
CuZn37Al1-B	UNI	Italy	Ingot and Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com