

Material: AFNOR NF P355Q

Standard Specification for Flat Products Made of Steels for Pressure Purposes

Group: Ferrous Mild Steel Alloys

Sub Group: AFNOR NF P355Q Flat Products Made of Steels for Pressure Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel

Chemical Composition		
Carbon	C %	0.160 max.
Silicon	Si %	0.400 max.
Manganese	Mn %	1.500 max.
Phosphorus	P %	0.025 max.
Sulphur	S %	0.010 max.
Chromium	Cr %	0.300 max.
Nickel	Ni %	0.500 max.
Molybdenum	Mo %	0.250 max.
Vanadium	V %	0.060 max.
Titanium	Ti %	0.030 max.
Niobium	Nb %	0.050 max.
Zirconium	Zr %	0.050 max.
Boron	B %	0.005 max.
Nitrogen	N %	0.015 max.
Iron	Fe %	Balance

Heat Treatment
Annealing or Normalizing or Hardening + Tempering

Mechanical Properties	
Tensile Strength in Mpa	490 - 630
Yield Strength in Mpa	315 min.
Elongation in %	22 min.
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	40 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.8830	EN	European Union	Steel
1.8866	DIN	Germany	Steel
C450L0	AS	Australia	Steel
4020	AISI	USA	Forging, Bar, Wire, and Shape
P355QH	UNI	Italy	Steel
C450	AS	Australia	Steel
A732 6N	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India