

Material: AFNOR NF X3CrNiN18-10

Standard Specification for Seamless Steel Tubes for Pressure Purposes

Group: Ferrous Stainless Steel Alloys

Sub Group: AFNOR NF X3CrNiN18-10 Seamless Steel Tubes for Pressure Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel and Tube

Chemical Composition		
Carbon	C %	0.030 max.
Silicon	Si %	0.750 max.
Manganese	Mn %	2.000 max.
Phosphorus	P %	0.040 max.
Sulphur	S %	0.015 max.
Chromium	Cr %	17.000 - 19.000
Nickel	Ni %	9.000 - 11.000
Nitrogen	N %	0.120 - 0.200
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
Solution Annealing

Mechanical Properties	
Tensile Strength in Mpa	570 - 770
Yield Strength in Mpa	270 min.
Elongation in %	40 min.
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.4311	EN	European Union	Tube
1.4311	DIN	Germany	Steel
1.4311	DIN	Germany	Steel
CrNi18/9-0.03C/N	BS	British	Steel and Flat
SUS 304 LN	JIS	Japan	Steel, Plate, Sheet and Strip
X20CrNiN 18-10	UNI	Italy	Sheet, Plate, Strip and Bar
X2CrNiN18 10 KKW	ONORM	Australia	Steel

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India