

Material: AISI 1552

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Bar

Group: Ferrous Mild Steel Alloys

Sub Group: AISI 1552 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Bar

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel and Bar

Chemical Composition			Heat Treatment	
Carbon	C %	0.470 - 0.550	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	1.200 - 1.500		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.050 max.		
Boron	B %	0.0005 - 0.003		
Aluminium	Al %	0.020 max.		
Copper	Cu %	0.200 max.		
Niobium	Nb %	0.015 max.		
Silicon	Si %	0.100 max.		
Vanadium	V %	0.020 max.		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	680 - 740
-	-	-	Yield Strength in Mpa	410 min.
-	-	-	Elongation in %	10 min.
-	-	-	Reduction of Area in %	30 - 40
-	-	-	Hardness in HB	193 - 217
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G15520	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1552	SAE	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
A 29 1552	ASTM	USA	Steel and Bar
A 510 1552	ASTM	USA	Wire Rod, Round Wire and Steel
A 830 1552	ASTM	USA	Plate and Steel
A 830 G15520	ASTM	USA	Plate and Steel
A 866 1552	ASTM	USA	Steel

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com