

## Material: AMS 430

### Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet and Strip for Pressure Vessels and for General Applications

**Group:** Ferrous Stainless Steel Alloys

**Sub Group:** AMS 430 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries

**Grade Belongs to the Industry:** Sheet, Bar, Wire, Shape and Forging

Chemical Composition			Heat Treatment	
Carbon	C %	0.120 max.	Annealing or Hardening + Tempering	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	16.000 - 18.000		
Iron	Fe %	Balance		
-	-	-		
-	-	-	<b>Mechanical Properties</b> Tensile Strength in Mpa 448 min. Yield Strength in Mpa 241 min. Elongation in % 15 min. Reduction of Area in % - Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A240 UNS S43000	ASTM	USA	Steel, Plate, Sheet and Strip
430	AISI	USA	Steel
430	AS	Australia	Steel, Sheet, Plate and Strip
430	SAE	USA	Sheet, Bar, Wire, Shape and Forging
STS 430	KS	Korea	Steel, Sheet, Plate and Strip
SUS 430	JIS	Japan	Steel, Wire and Bar
A182 F 430	ASTM	USA	Steel, Pipe and Forging

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)