

Material: AMS 5351

Standard Specification for Steel Castings, Sand, Corrosion and Moderate Heat Resistant 13Cr Normalized and Tempered

Group: Ferrous Stainless Steel Alloys

Sub Group: AMS 5351 Steel Castings, Sand, Corrosion and Moderate Heat Resistant 13Cr Normalized and Tempered

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition		
Carbon	C %	0.150 max.
Silicon	Si %	1.500 max.
Manganese	Mn %	1.000 max.
Phosphorus	P %	0.040 max.
Sulphur	S %	0.030 max.
Chromium	Cr %	11.500 - 14.000
Nickel	Ni %	1.000 max.
Molybdenum	Mo %	0.500 max.
Aluminium	Al %	0.050 max.
Tin	Sn %	0.050 max.
Copper	Cu %	0.500 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-

Heat Treatment	
	Annealing or Hardening + Tempering

Mechanical Properties	
Tensile Strength in Mpa	620 min.
Yield Strength in Mpa	-
Elongation in %	-
Reduction of Area in %	-
Hardness in HB	217 - 248
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
410	AISI	USA	Bar, Wire, Shapes and Forging
410 C 21	BS	British	Casting
15ch13L	GOST	Russia	Casting
385 G X 12 Cr 13	SFS	Finland	Casting
A217 CA 15	ASTM	USA	Casting
A 487 CA 15	ASTM	USA	Casting
A743 CA 15	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India