

Material: ANSI/AA C85800

Specification Standards for Die Castings

Group: Non-Ferrous Copper Alloy Sub

Group: ANSI/AA for Die Castings

Application : Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Tin	Sn %	1.500 max.	As-Cast	
Lead	Pb %	1.500 max.		
Zinc	Zn %	31.000 - 41.000		
Iron	Fe %	0.500 max.		
Aluminium	Al %	0.550 max.		
Manganese	Mn %	0.250 max.		
Antimony	Sb %	0.050 max.		
Nickel	Ni %	0.500 max.		
Sulphur	S %	0.050 max.		
Phosphorus	P %	0.010 max.		
Silicon	Si %	0.250 max.	Mechanical Properties	
Arsenic	As %	0.050 max.	Tensile Strength in Mpa	379 min.
Other	Ot%	1.000 max.	Yield Strength in Mpa	207 min.
Copper	Cu %	57.000 min.	Elongation in %	15 min.
-	-	-	Reduction of Area in %	-
			Hardness in BHN	55 min.
			Impact in Joule	54 min.

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com