

Material: ANSI/AA 43

Standard Specification for Aluminium Alloy for General Engineering and Light-Weight Structural Purpose

Group: Non-Ferrous Aluminium Alloy

Sub Group: ANSI/AA Aluminium Alloy for General Engineering and Light-Weight Structural Purpose

Application : Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Silicon	Si %	4.500 - 6.000	As-Cast	
Iron	Fe %	2.000 max.		
Copper	Cu %	0.600 max.		
Magnesium	Mg %	0.100 max.		
Manganese	Mn %	0.350 max.		
Nickel	Ni %	0.500 max.		
Zinc	Zn %	0.500 max.		
Tin	Sn %	0.150 max.		
Other	Ot%	0.250 max.		
Aluminium	Al %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 228 min. Yield Strength in Mpa 97 min. Elongation in % 9 min. Reduction of Area in % - Hardness in BHN 65 min. Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B179 443.1	ASTM	USA	Casting
B275 443.1	ASTM	USA	Casting
A04431	UNS	USA	Casting
A04430	UNS	USA	Casting
SB-108 AA3.0	ASME	USA	Casting
A413.0	NBR	Brazil	Casting
A413.0	NMX	Maxico	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com