

Material: ANSI/AA B390

Standard Specification for Aluminium Alloy for General Engineering and Light-Weight Structural Purpose

Group: Non-Ferrous Aluminium Alloy

Sub Group: ANSI/AA Aluminium Alloy for General Engineering and Light-Weight Structural Purpose

Application : Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Silicon	Si %	16.000 - 18.000	As-Cast	
Iron	Fe %	1.300 max.		
Copper	Cu %	4.000 - 5.000		
Magnesium	Mg %	0.450 - 0.650		
Manganese	Mn %	0.500 max.		
Nickel	Ni %	0.100 max.		
Zinc	Zn %	1.500 max.		
Titanium	Ti %	0.100 max.		
Other	Ot%	0.200 max.		
Aluminium	Al %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	317 min.
-	-	-	Yield Strength in Mpa	248 min
-	-	-	Elongation in %	1 max.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	120 min.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN AC-48100	DIN	Germany	Casting
EN AC-48100	ASME	USA	Casting
EN AC-48100	UNI	Italy	Casting
EN AC-48100	AFNOR NF	France	Casting
EN AC-48100	UNE	Spain	Casting
EN AC-48100	SFS	Finland	Casting
EN AC-48100	MSZ	Hungary	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com

ICAST ALLOYS LLP



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India