

Material: AS 1874 307

Standard Specification for Aluminium and Aluminium Alloy - Ingot and Castings

Group: Non-Ferrous Aluminium Alloy

Sub Group: AS 1874 Aluminium and Aluminium Alloy - Ingot and Castings

Application : Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Ingot and Casting

Chemical Composition			Heat Treatment															
Copper	Cu %	0.700 - 2.500	As-Cast															
Iron	Fe %	1.000 max.																
Magnesium	Mg %	0.300 max.																
Manganese	Mn %	0.500 max.																
Nickel	Ni %	0.500 max.																
Lead	Pb %	0.350 max.																
Silicon	Si %	9.000 - 11.500																
Tin	Sn %	0.250 max.																
Zinc	Zn %	2.000 max.																
Chromium	Cr %	0.100 max.																
Titanium	Ti %	0.200 max.																
Other	Ot%	0.200 max.																
Aluminium	Al %	Balance																
-	-	-	<table border="1"> <thead> <tr> <th colspan="2">Mechanical Properties</th> </tr> </thead> <tbody> <tr> <td>Tensile Strength in Mpa</td> <td>-</td> </tr> <tr> <td>Yield Strength in Mpa</td> <td>-</td> </tr> <tr> <td>Elongation in %</td> <td>-</td> </tr> <tr> <td>Reduction of Area in %</td> <td>-</td> </tr> <tr> <td>Hardness in BHN</td> <td>-</td> </tr> <tr> <td>Impact in Joule</td> <td>-</td> </tr> </tbody> </table>		Mechanical Properties		Tensile Strength in Mpa	-	Yield Strength in Mpa	-	Elongation in %	-	Reduction of Area in %	-	Hardness in BHN	-	Impact in Joule	-
Mechanical Properties																		
Tensile Strength in Mpa	-																	
Yield Strength in Mpa	-																	
Elongation in %	-																	
Reduction of Area in %	-																	
Hardness in BHN	-																	
Impact in Joule	-																	
-	-	-																

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
AA307	AS	Australia	Ingot and Casting
LM2	BS	British	Ingot and Casting
4520	IS	India	Ingot and Casting
ADC12	JIS	Japan	Ingot and Casting
ADC12Z	JIS	Japan	Ingot and Casting
383	AA	USA	Ingot and Casting
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com