

Material: AS 1874 CA327

Standard Specification for Aluminium and Aluminium Alloys - Ingots and Castings

Group: Non-Ferrous Aluminium Alloy

Sub Group: AS 1874 Aluminium and Aluminium Alloys - Ingots and Castings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Ingot and Casting

Chemical Composition			Heat Treatment	
Copper	Cu %	3.000 - 4.000	As-Cast	
Iron	Fe %	0.250 max.		
Magnesium	Mg %	0.100 - 0.180		
Manganese	Mn %	0.500 max.		
Nickel	Ni %	0.100 max.		
Silicon	Si %	5.500 - 6.800		
Titanium	Ti %	0.150 max.		
Zinc	Zn %	0.100 max.		
Aluminium	Al %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	155 - 230
			Yield Strength in Mpa	-
			Elongation in %	1 - 1.5
			Reduction of Area in %	-
			Hardness in HB	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
ADC 8	JIS	Japan	Casting
LM21	BS	British	Casting
319.0	AA	USA	Ingot and Casting
308.0	AA	USA	Ingot and Casting
B 108 308.0	ASTM	USA	Casting
SB-108 308.0	ASME	USA	Casting
A03080	UNS	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com