

Material: AS 2074/L1A

Standard Specification for Steel Castings for General Engineering Purposes

Group: Ferrous Mild Steel Alloys

Sub Group: AS 2074/L1A Steel Castings for General Engineering Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition		
Carbon	C %	0.180 - 0.250
Silicon	Si %	0.600 max.
Manganese	Mn %	1.200 - 1.600
Phosphorus	P %	0.050 max.
Sulphur	S %	0.050 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As Cast or Annealing or Normalizing or Hardening and Tempering

Mechanical Properties	
Tensile Strength in Mpa	540 min.
Yield Strength in Mpa	340 min.
Elongation in %	13 min.
Reduction of Area in %	-
Hardness in BHN	152 - 207
Impact in Joule	27 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A4	BS	British	Casting
2708 Grade 1	IS	India	Casting
1524	SAE	USA	Casting
1524	AISI	USA	Casting
A 29 1524	ASTM	USA	Bar
A 510 1524	ASTM	USA	Wire and Rod
A 519 1524	ASTM	USA	Tube

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India