

Material: AS 2738 C85400

Standard Specification for Copper and Copper Alloys - Compositions and Designations of Refinery Products, Wrought Products, Ingots and Castings

Group: Non-Ferrous Copper Alloy

Sub Group: AS 2738 Copper and Copper Alloys - Compositions and Designations of Refinery Products, Wrought Products, Ingots and Castings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.350 max.	As-Cast	
Iron	Fe %	0.700 max.		
Nickel	Ni %	1.000 max.		
Lead	Pb %	1.500 - 3.800		
Silicon	Si %	0.050 max.		
Tin	Sn %	0.500 - 1.500		
Zinc	Zn %	24.000 - 32.000		
Copper	Cu %	65.000 - 70.000		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	190 min.
-	-	-	Yield Strength in Mpa	70 min.
-	-	-	Elongation in %	11 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	45 min.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
SCB3	BS	British	Casting
854C	AS	Australia	Ingot and Casting
CuZn33Pb2	ISO	International	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com