

Material: AS 2738 C95710

Standard Specification for Copper and Copper Alloys - Compositions and Designations of Refinery Products, Wrought Products, Ingots and Castings

Group: Non-Ferrous Copper Alloy

Sub Group: AS 2738 Copper and Copper Alloys - Compositions and Designations of Refinery Products, Wrought Products, Ingots and Castings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	7.000 - 8.500	As-Cast	
Iron	Fe %	2.000 - 4.000		
Manganese	Mn %	11.000 - 14.000		
Nickel	Ni %	1.500 - 3.000		
Phosphorus	P %	0.050 max.		
Lead	Pb %	0.050 max.		
Silicon	Si %	0.150 max.		
Tin	Sn %	1.000 max.		
Zinc	Zn %	0.500 max.		
Copper	Cu %	71.000 min.	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	680 min.
-	-	-	Yield Strength in Mpa	280 min.
-	-	-	Elongation in %	18 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	160 min.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CMA1	BS	British	Ingot and Casting
957B	AS	Australia	Ingot and Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com