

Material: AS 316Ti

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet and Strip for Pressure Vessels and for General Applications

Group: Ferrous Stainless Steel Alloys

Sub Group: AS 316Ti Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel, Plate, Sheet and Strip

Chemical Composition		
Carbon	C %	0.080 max.
Silicon	Si %	0.750 max.
Manganese	Mn %	2.000 max.
Phosphorus	P %	0.045 max.
Sulphur	S %	0.030 max.
Chromium	Cr %	16.000 - 18.000
Molybdenum	Mo %	2.000 - 3.000
Nickel	Ni %	10.000 - 14.000
Titanium	Ti %	0.700 max.
Copper	Cu %	0.350 max.
Nitrogen	N %	0.100 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-

Heat Treatment	
Solution Annealing	

Mechanical Properties	
Tensile Strength in Mpa	520 min.
Yield Strength in Mpa	205 min.
Elongation in %	40 min.
Reduction of Area in %	-
Hardness in HB	217 max.
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A240 UNS S31635	ASTM	USA	Steel, Plate, Sheet and Strip
316Ti	SAE	USA	Steel
STS 316 Ti	KS	Korea	Steel, Sheet, Plate and Strip
SUS 316 Ti	JIS	Japan	Steel, Wire and Rod
A276 316 Ti	ASTM	USA	Steel, Bar and Shapes
A314 316 Ti	ASTM	USA	Steel, Bar, Rolling and Forging
A479 316 Ti	ASTM	USA	Steel and Bar

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India