

Material: AS/NZS 1565 C85400

Standard Specification for Copper and Copper Alloys - Ingot and Casting

Group: Non-Ferrous Copper Alloy

Sub Group: AS/NZS 1565 Copper and Copper Alloys - Ingot and Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Ingot and Casting

Chemical Composition		
Aluminium	Al %	0.350 max.
Iron	Fe %	0.700 max.
Nickel	Ni %	1.000 max.
Lead	Pb %	1.500 - 3.800
Silicon	Si %	0.050 max.
Tin	Sn %	0.500 - 1.500
Zinc	Zn %	24.000 - 32.000
Copper	Cu %	65.000 - 70.000
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Cast

Mechanical Properties	
Tensile Strength in Mpa	190 min.
Yield Strength in Mpa	70 min.
Elongation in %	11 min.
Reduction of Area in %	-
Hardness in HB	45 min.
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
C85400	UNS	USA	Rod, Bar, Tube and Shapes
B30 C85400	ASTM	USA	Ingot and Casting
B271 C85400	ASTM	USA	Casting
B584 C85400	ASTM	USA	Casting
C85400	SAE	USA	Casting
CA854	SAE	USA	Casting
CACIn202	KS	Korea	Ingot and Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 **Email:** info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India