

Standard Specification for Copper and Copper-Alloy Forgings

Sub Group: *AS/NZS 1568 Copper and Copper-Alloy Forgings*

Belongs to the Industry: *Forging*

Chemical Composition			Heat Treatment	
Iron	Fe %	0.150 max.	Normalizing or Annealing or Tempering	
Lead	Pb %	0.250 - 0.700		
Tin	Sn %	0.250 max.		
Copper	Cu %	58.000 - 61.000		
Zinc	Zn %	Balance		
-	-	-		
-	-	-		
-	-	-	Mechanical Properties	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Tensile Strength in Mpa	310 min.
			Yield Strength in Mpa	-
			Elongation in %	25 min.
			Reduction of Area in %	-
			Hardness in BHN	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B171 C36500	ASTM	USA	Plate and Sheet
B283 C36500	ASTM	USA	Forging
SB-171 C36500	ASME	USA	Plate and Sheet
SB-283 C36500	ASME	USA	Forging
C36500	AS	Australia	Forging
C36500	UNS	USA	Rod, Bar and Shapes
B124 C36500	ASTM	USA	Rod, Bar and Shapes

Customer Care: +91-99090 45075 Email: info@icastllp.com