

Material: ASME SA-240 UNS S40900

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet and Strip for Pressure Vessels and for General Applications

Group: Ferrous Stainless Steel Alloys

Sub Group: ASME SA-240 UNS S40900 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel

Chemical Composition		
Carbon	C %	0.080 max.
Silicon	Si %	1.000 max.
Manganese	Mn %	1.000 max.
Phosphorus	P %	0.040 max.
Sulphur	S %	0.020 max.
Chromium	Cr %	10.500 - 11.700
Nickel	Ni %	0.500 max.
Nitrogen	N %	0.030 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment	
	Annealing or Hardening + Tempering

Mechanical Properties	
Tensile Strength in Mpa	380 min.
Yield Strength in Mpa	170 min.
Elongation in %	20 min.
Reduction of Area in %	-
Hardness in BHN	179 max.
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A240 UNS S40900	ASTM	USA	Steel, Plate, Sheet and Strip
S409000	UNS	USA	Steel
409	AS	Australia	Steel, Sheet, Plate and Strip
409	SAE	USA	Steel
STS 409LTP	KS	Korea	Steel and Pipe
SUH 409	JIS	Japan	Steel, Plate and Sheet
409 S 19	BS	British	Steel, Sheet, Plate and Strip

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India