

Material: ASME SA-240 UNS S44500

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet and Strip for Pressure Vessels and for General Applications

Group: Ferrous Stainless Steel Alloys

Sub Group: ASME SA-240 UNS S44500 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel, Sheet, Plate and Strip

Chemical Composition		
Carbon	C %	0.020 max.
Silicon	Si %	1.000 max.
Manganese	Mn %	1.000 max.
Phosphorus	P %	0.045 max.
Sulphur	S %	0.012 max.
Chromium	Cr %	19.000 - 21.000
Nickel	Ni %	0.600 max.
Nitrogen	N %	0.030 max.
Copper	Cu %	0.300 - 0.600
Niobium	Nb %	0.800 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
Annealing or Hardening + Tempering

Mechanical Properties	
Tensile Strength in Mpa	427 min.
Yield Strength in Mpa	205 min.
Elongation in %	22 min.
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A240 UNS S44500	ASTM	USA	Steel, Plate, Sheet and Strip
S44500	UNS	USA	Steel
A959 S44500	ASTM	USA	Steel
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India