

Material: ASME SA-351 CN3MN

Standard Specification for Austenitic Steel Castings for Valves, Flanges, Fittings, and Other Pressure-Containing Parts

Group: Ferrous Stainless Steel Alloys

Sub Group: ASME SA-351 CN3MN Austenitic Steel Castings for Valves, Flanges, Fittings, and Other Pressure-Containing Parts

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.	Solution Annealing	
Silicon	Si %	1.000 max.		
Manganese	Mn %	2.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.010 max.		
Chromium	Cr %	20.000 - 22.000		
Nickel	Ni %	23.500 - 25.500		
Molybdenum	Mo %	6.000 - 7.000		
Copper	Cu %	0.750 max.		
Nitrogen	N %	0.180 - 0.260		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Tensile Strength in Mpa	550 min.
			Yield Strength in Mpa	260 min.
			Elongation in %	35 min.
			Reduction of Area in %	-
			Hardness in BHN	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.4585	DIN	Germany	Casting
J94651	UNS	USA	Casting
Ao X 10 CrNiMoCuNb 18-18	MSZ	Hungary	Casting
G X 7 CrNiMoCuNb 18-18	DIN	Germany	Casting
A351 CN3MN	ASTM	USA	Casting
A743 CN3MN	ASTM	USA	Casting
A744 CN3MN	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com