

Material: ASME SA-487 Class CA6NM

Standard Specification for Martenistic Steel Castings Suitable for Pressure Service

Group: Ferrous Stainless Steel Alloys

Sub Group: SA-487 Martenistic Steel Castings Suitable for Pressure Service

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.060 max.	Heating + Reheating + Aging	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	11.500 - 14.000		
Nickel	Ni %	3.500 - 4.500		
Molybdenum	Mo %	0.400 - 1.000		
Vanadium	V %	0.030 max.		
Tungsten	W %	0.100 max.		
			Mechanical Properties	
Copper	Cu %	0.500 max.	Tensile Strength in Mpa	760 - 930
Iron	Fe %	Balance	Yield Strength in Mpa	550 min.
-	-	-	Elongation in %	15 min.
-	-	-	Reduction of Area in %	35 min.
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
ASME SA-487 CA6NMa	ASME	USA	Casting
ASME SA-487 CA6NMb	ASME	USA	Casting
ASME SA-352 CA6NM	ASME	USA	Casting
A 352 CA6NM	ASTM	USA	Casting
A 356 CA6NM	ASTM	USA	Casting
A 487 CA6NM	ASTM	USA	Casting
A743 CA6NM	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com