

Material: ASME SA-487 Garde 16A

Standard Specification for Low Alloy Steel and Martensitic Stainless Steel Castings Suitable for Pressure Containing Parts

Group: Ferrous Mild Steel Alloys

Sub Group: ASME SA-487 Garde 16A Low Alloy Steel and Martensitic Stainless Steel Castings Suitable for Pressure Containing Parts

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.120 max.	Annealing or Normalizing or Hardening + Tempering	
Silicon	Si %	0.500 max.		
Manganese	Mn %	2.100 max.		
Phosphorus	P %	0.020 max.		
Sulphur	S %	0.020 max.		
Chromium	Cr %	0.200 max.		
Nickel	Ni %	1.000 - 1.400		
Molybdenum	Mo %	0.100 max.		
Tungsten	W %	0.100 max.		
Copper	Cu %	0.200 max.		
Vanadium	V %	0.020 max.	Mechanical Properties	
Iron	Fe %	Balance	Tensile Strength in Mpa	485 - 655
-	-	-	Yield Strength in Mpa	275 min.
-	-	-	Elongation in %	22 min.
-	-	-	Reduction of Area in %	35 min.
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
J31200	UNS	USA	Casting
1.6222	DIN	Germany	Steel
1.8932	EN	European Union	Forging
E 460 DD	JIS	Japan	Plate
P 420 NH	EN	European Union	Forging
9 NiMn 5	DIN	Germany	Steel
A487 16A	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com