

Material: ASME SA-487 Grade 8 Class C

Standard Specification for Low Alloy Steel and Martensitic Stainless Steel Castings Suitable for Pressure Containing Parts

Group: Ferrous Mild Steel Alloys

Sub Group: ASME SA-487 Grade 8 Class C Low Alloy Steel and Martensitic Stainless Steel Castings Suitable for Pressure Containing Parts

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition		
Carbon	C %	0.050 - 0.200
Silicon	Si %	0.800 max.
Manganese	Mn %	0.500 - 0.900
Phosphorus	P %	0.040 max.
Sulphur	S %	0.045 max.
Chromium	Cr %	2.000 - 2.750
Molybdenum	Mo %	0.900 - 1.100
Vanadium	V %	0.030 max.
Tungsten	W %	0.100 max.
Copper	Cu %	0.500 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
Annealing or Normalizing or Hardening + Tempering

Mechanical Properties	
Tensile Strength in Mpa	690 min.
Yield Strength in Mpa	515 min.
Elongation in %	17 min.
Reduction of Area in %	35 min.
Hardness in HB	235 max.
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
SA-487 Class 8N	ASME	USA	Casting
SA-487 Grade 8A	ASME	USA	Casting
SA-487 Grade 8B	ASME	USA	Casting
J220911	UNS	USA	Casting
A487 8A	ASTM	USA	Casting
A487 8B	ASTM	USA	Casting
A487 8C	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com