

Material: ASME SA-487 Grade CA6NM Class B

Standard Specification for Low Alloy Steel and Martensitic Stainless Steel Castings Suitable for Pressure Containing Parts

Group: Ferrous Stainless Steel Alloys

Sub Group: ASME SA-487 Grade CA6NM Class B Low Alloy Steel and Martensitic Stainless Steel Castings Suitable for Pressure Containing Parts

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.060 max.	Heating + Reheating + Aging	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	11.500 - 14.000		
Nickel	Ni %	3.500 - 4.500		
Molybdenum	Mo %	0.400 - 1.000		
Vanadium	V %	0.050 max.		
Tungsten	W %	0.100 max.		
Copper	Cu %	0.500 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	690 min.
			Yield Strength in Mpa	515 min.
			Elongation in %	17 min.
			Reduction of Area in %	35 min.
			Hardness in BHN	255 max.
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
ASME SA-487 CA6NMa	ASME	USA	Casting
ASME SA-352 CA6NM	ASME	USA	Casting
ASME SA-487 Class CA6NM	ASME	USA	Casting
A 352 CA6NM	ASTM	USA	Casting
A 356 CA6NM	ASTM	USA	Casting
A 487 CA6NM	ASTM	USA	Casting
A743 CA6NM	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com