

Material: ASME SA217 Grade WC1

Standard Specification for Martensitic Stainless Steel and Alloy Steel Castings for Pressure Containing Parts Suitable for High Temperature Service

Group: Ferrous Mild Steel Alloys

Sub Group: ASME SA217 Grade WC1 Martensitic Stainless Steel and Alloy Steel Castings for Pressure Containing Parts Suitable for High Temperature Service

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition		
Carbon	C %	0.250 max.
Silicon	Si %	0.600 max.
Manganese	Mn %	0.500 - 0.800
Phosphorus	P %	0.040 max.
Sulphur	S %	0.045 max.
Chromium	Cr %	0.350 max.
Molybdenum	Mo %	0.450 - 0.650
Nickel	Ni %	0.500 max.
Copper	Cu %	0.500 max.
Tungsten	W %	0.100 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment	
Normalizing or Annealing or Hardening + Tempering	

Mechanical Properties	
Tensile Strength in Mpa	450 - 620
Yield Strength in Mpa	240 min.
Elongation in %	24 min.
Reduction of Area in %	35 min.
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
J12524	UNS	USA	Casting
G20 Mo 5	EN	European Union	Casting
SCPH 11	JIS	Japan	Casting
A352 LC1	ASTM	USA	Casting
G 20 MO5	DIN	Germany	Casting
G 20 MO5	UNI	Italy	Casting
A217 Grade WC1	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India