

Material: ASME SB-150 C61900

Specification for Aluminum Bronze Rod, Bar and Shapes

Group: Non-Ferrous Copper Alloy

Sub Group: ASME SB-150 Aluminum Bronze Rod, Bar and Shapes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Rod, Bar and Shapes

Chemical Composition			Heat Treatment	
Aluminium	Al %	8.500 - 10.000	As Drawn or Stress Relieving or Hot Rolled	
Iron	Fe %	3.000 - 4.500		
Lead	Pb %	0.020 max.		
Tin	Sn %	0.600 max.		
Zinc	Zn %	0.800 max.		
Cu + Ag	Cu% + Ag%	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 515 - 620 Yield Strength in Mpa 205 - 345 Elongation in % 15 - 25 Reduction of Area in % - Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
C61900	UNS	USA	Rod, Bar, Tube and Shapes
B124 C61900	ASTM	USA	Rod, Bar and Shapes
B150 C61900	ASTM	USA	Rod, Bar and Shapes
B283 C61900	ASTM	USA	Forging
SB-283 C61900	ASME	USA	Forging
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com