

Material: ASME SB-150 C64200

Standard Specification for Aluminum Bronze Rod, Bar and Shapes

Group: Non-Ferrous Copper Alloy

Sub Group: ASME SB-150 Aluminum Bronze Rod, Bar and Shapes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Rod, Bar and Shape

Chemical Composition			Heat Treatment	
Aluminium	Al %	6.300 - 7.600	As Drawn or Stress Relieving or Hot Rolled	
Arsenic	As %	0.150 max.		
Iron	Fe %	0.300 max.		
Manganese	Mn %	0.100 max.		
Ni + Co	Ni% + Co%	0.250 max.		
Lead	Pb %	0.050 max.		
Silicon	Si %	1.500 - 2.200		
Tin	Sn %	0.200 max.		
Zinc	Zn %	0.500 max.		
Cu + Ag	Cu% + Ag%	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 485 - 620 Yield Strength in Mpa 170 - 310 Elongation in % 9 - 15 Reduction of Area in % - Hardness in HRB 65 - 100 Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
C64200	UNS	USA	Rod, Bar, Tube and Shapes
B124 C64200	ASTM	USA	Rod, Bar and Shape
B283 C64200	ASTM	USA	Forging
SB-283 C64200	ASME	USA	Forging
4264	SAE	USA	Rod, Bar and Forging
4633	SAE	USA	Rod, Bar and Forging
4634	SAE	USA	Rod, Bar and Forging

Disclaimer: **All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.**

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India