

Material: ASME SB-434 N10003

Standard Specification for Nickel-Molybdenum-Chromium-Iron Alloys Plate, Sheet and Strip

Group: Non-Ferrous Nickel Alloys

Sub Group: ASME SB-434 N10003 Nickel-Molybdenum-Chromium-Iron Alloys Plate, Sheet and Strip

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Plate, Sheet and Strip

Chemical Composition			Heat Treatment	
Carbon	C %	0.040 - 0.080	As-Cast or Annealing or Age Hardning	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Chromium	Cr %	6.000 - 8.000		
Sulphur	S %	0.020 max.		
Molybdenum	Mo %	15.000 - 18.000		
Phosphorus	P %	0.015 max.		
Cobalt	Co %	0.200 max.		
Copper	Cu %	0.350 max.		
Iron	Fe %	5.000 max.		
			Mechanical Properties	
Boron	B %	0.010 max.	Tensile Strength in Mpa	690 min.
Tungsten	W %	0.500 max.	Yield Strength in Mpa	280 min.
Vanadium	V %	0.500 max.	Elongation in %	40 min.
Al + Ti	Al % + Ti %	0.500 max.	Reduction of Area in %	-
Nickel	Ni %	Balance	Hardness in BHN	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 434 N10003	ASTM	USA	Plate, Sheet and Strip
B 573 N10003	ASTM	USA	Rod
SB-573 N10003	ASME	USA	Rod
N10003	UNS	USA	Rod
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com