

Material: ASME SB-505 C94800

Standard Specification for Copper Alloy Continuous Casting

Group: Non-Ferrous Copper Alloy

Sub Group: ASME SB-505 Copper Alloy Continuous Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment			
Aluminium	Al %	0.005 max.	As-Cast			
Iron	Fe %	0.250 max.				
Manganese	Mn %	0.200 max.				
Ni + Co	Ni% + Co%	4.500 - 6.000				
Phosphorus	P %	0.050 max.				
Lead	Pb %	0.300 - 1.000				
Sulphur	S %	0.050 max.				
Antimony	Sb %	0.150 max.				
Silicon	Si %	0.005 max.				
Tin	Sn %	4.500 - 6.000				
Zinc	Zn %	1.000 - 2.500	Mechanical Properties			
Copper	Cu %	84.000 - 89.000			Tensile Strength in Mpa	276 min.
-	-	-			Yield Strength in Mpa	138 min.
-	-	-			Elongation in %	20 min.
-	-	-			Reduction of Area in %	-
-	-	-	Hardness in BHN	-		
-	-	-	Impact in Joule	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
C94800	UNS	USA	Rod, Bar, Tube and Shapes
B292-B	ASTM	USA	Casting
B30 C94800	ASTM	USA	Ingot and Casting
B505 C94800	ASTM	USA	Casting
B584 C94800	ASTM	USA	Casting
C94800	SAE	USA	Casting
CA948	SAE	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com