

Material: ASME SB-505 C95500

Standard Specification for Copper Alloy Continuous Casting

Group: Non-Ferrous Copper Alloy

Sub Group: ASME SB-505 Copper Alloy Continuous Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	10.000 - 11.500	As-Cast or Solution Annealing or Annealing	
Iron	Fe %	3.000 - 5.000		
Manganese	Mn %	3.500 max.		
Ni + Co	Ni% + Co%	3.000 - 5.500		
Copper	Cu %	78.000 min.		
-	-	-		
-	-	-		
-	-	-		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	655 - 758
-	-	-	Yield Strength in Mpa	290 - 427
-	-	-	Elongation in %	8 - 10
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
C95500	UNS	USA	Rod, Bar, Tube and Shapes
B148 C95500	ASTM	USA	Casting
B30 C95500	ASTM	USA	Ingot and Casting
B271 C95500	ASTM	USA	Casting
SB-148 C95500	ASME	USA	Casting
CA955	SAE	USA	Casting
C95500	SAE	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com