

Material: ASME SB-564 N02200

Standard Specification for Nickel Alloy Forgings

Group: Non-Ferrous Nickel Alloys

Sub Group: ASME SB-564 N02200 Nickel Alloy Forgings

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Forging

Chemical Composition		
Carbon	C %	0.150 max.
Silicon	Si %	0.350 max.
Manganese	Mn %	0.350 max.
Copper	Cu %	0.250 max.
Sulphur	S %	0.010 max.
Iron	Fe %	0.400 max.
Nickel	Ni %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	0	-

Heat Treatment
As-Cast or Annealing or Age Hardning

Mechanical Properties	
Tensile Strength in Mpa	380 min.
Yield Strength in Mpa	105 min.
Elongation in %	40 min.
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 564 N02200	ASME	USA	Forging
SB-725 N02200	ASME	USA	Pipe
B 725 N02200	ASTM	USA	Pipe
B 160 N02200	ASTM	USA	Rod and Bar
B 161 N02200	ASTM	USA	Pipe and Tube
B 162 N02200	ASTM	USA	Plate, Sheet and Strip
B 163 N02200	ASTM	USA	Tube

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India