

Material: ASME SB-572 N06230

Standard Specification for Nickel and Nickel-Related Alloys Plate, Sheet and Strip

Group: Non-Ferrous Nickel Alloys

Sub Group: ASME SB-572 N06230 Nickel and Nickel-Related Alloys Plate, Sheet and Strip

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Sheet, Strip and Plate

Chemical Composition			Heat Treatment	
Carbon	C %	0.005 - 0.150	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.250 - 0.750		
Manganese	Mn %	0.300 - 1.000		
Chromium	Cr %	20.000 - 24.000		
Cobalt	Co %	5.000 max.		
Molybdenum	Mo %	1.000 - 3.000		
Sulphur	S %	0.015 max.		
Phosphorus	P %	0.030 max.		
Aluminium	Al %	0.500 max.		
Iron	Fe %	3.000 max.		
Boron	B %	0.015 max.	Mechanical Properties Tensile Strength in Mpa 760 min. Yield Strength in Mpa 310 min. Elongation in % 40 min. Reduction of Area in % - Hardness in BHN - Impact in Joule -	
Lanthanum	La %	0.005 - 0.050		
Tungsten	W %	13.000 - 15.000		
Nickel	Ni %	Balance		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
UNS N06230	UNS	USA	Sheet, Strip and Plate
INCONEL alloy N06230	Gravity	India	Sheet, Strip and Plate
B472 N06230	ASTM	USA	Billets and Bars for Reforging
B435 N06230	ASTM	USA	Plate, Sheet and Strip
B564 N06230	ASTM	USA	Forging
SB-435 N06230	ASME	USA	Plate, Sheet and Strip
SB-564 N06230	ASME	USA	Forging

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com