

Material: ASME SB-581 N06007

Standard Specification for Nickel-Chromium-Iron-Molybdenum-Copper Alloy Rod

Group: Non-Ferrous Nickel Alloys

Sub Group: ASME SB-581 N06007 Nickel-Chromium-Iron-Molybdenum-Copper Alloy Rod

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Rod

Chemical Composition			Heat Treatment	
Carbon	C %	0.050 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 - 2.000		
Chromium	Cr %	21.000 - 23.500		
Sulphur	S %	0.030 max.		
Molybdenum	Mo %	5.500 - 7.500		
Phosphorus	P %	0.040 max.		
Cobalt	Co %	2.500 max.		
Iron	Fe %	18.000 - 21.000		
			Mechanical Properties	
Copper	Cu %	1.500 - 2.500	Tensile Strength in Mpa	586 min.
Tungsten	W %	1.000 max.	Yield Strength in Mpa	207 min.
Nitrogen	N %	0.150 - 0.250	Elongation in %	30 min.
Nb + Ta	Nb% + Ta%	1.750 - 2.500	Reduction of Area in %	-
Nickel	Ni %	Balance	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 581 N06007	ASTM	USA	Rod
B 582 N06007	ASTM	USA	Plate, Sheet and Strip
B 619 N06007	ASTM	USA	Pipe
B 622 N06007	ASTM	USA	Pipe and Tube
B 626 N06007	ASTM	USA	Tube
SB-619 N06007	ASME	USA	Pipe
SB-626 N06007	ASME	USA	Tube

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India