

Material: ASME SB-581 N06985

Standard Specification for Nickel-Chromium-Iron-Molybdenum-Copper Alloy Rod

Group: Non-Ferrous Nickel Alloys

Sub Group: ASME SB-581 N06985 Nickel-Chromium-Iron-Molybdenum-Copper Alloy Rod

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Rod

Chemical Composition			Heat Treatment	
Carbon	C %	0.015 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Chromium	Cr %	21.000 - 23.500		
Sulphur	S %	0.030 max.		
Molybdenum	Mo %	6.000 - 8.000		
Phosphorus	P %	0.040 max.		
Nb + Ta	Nb% + Ta%	0.500 max.		
Tungsten	W %	1.500 max.		
Copper	Cu %	1.500 - 2.500		
Cobalt	Co %	5.000 max.	Mechanical Properties	
Iron	Fe %	18.000 - 21.000	Tensile Strength in Mpa	586 min.
Nickel	Ni %	Balance	Yield Strength in Mpa	207 min.
-	-	-	Elongation in %	35 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 582 N06985	ASTM	USA	Plate, Sheet and Strip
B 619 N06985	ASTM	USA	Pipe
B 622 N06985	ASTM	USA	Pipe and Tube
B 626 N06985	ASTM	USA	Tube
SB-581 N06985	ASME	USA	Rod
SB-582 N06985	ASME	USA	Plate, Sheet and Strip
SB-619 N06985	ASME	USA	Pipe

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com