

# Material: ASME SB-584 C85700

## Standard Specification for Copper Alloy Sand Casting for General Applications

**Group:** Non-Ferrous Copper Alloy

**Sub Group:** ASME SB-584 Copper Alloy Sand Casting for General Applications

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

**Belongs to the Industry:** Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.800 max.	As-Cast	
Iron	Fe %	0.700 max.		
Ni + Co	Ni% + Co%	1.000 max.		
Lead	Pb %	0.800 - 1.500		
Silicon	Si %	0.050 max.		
Tin	Sn %	0.500 - 1.500		
Zinc	Zn %	32.000 - 40.000		
Copper	Cu %	58.000 - 64.000		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	276 min.
-	-	-	Yield Strength in Mpa	97 min.
-	-	-	Elongation in %	15 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
C85700	UNS	USA	Rod, Bar, Tube and Shapes
B176 C85700	ASTM	USA	Casting
B271 C85700	ASTM	USA	Casting
B30 C85700	ASTM	USA	Ingot and Casting
B505 C85700	ASTM	USA	Casting
B584 C85700	ASTM	USA	Casting
CACIn203	KS	Korea	Casting

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

**Customer Care:** +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)