

Material: ASME SB-637 N07080

Standard Specification for Precipitation-Hardening and Cold Worked Nickel Alloy Bars, Forgings, and Forging Stock for Moderate or High Temperature Service

Group: Non-Ferrous Nickel Alloys

Sub Group: ASME SB-637 N07080 Precipitation-Hardening and Cold Worked Nickel Alloy Bars, Forgings, and Forging Stock for Moderate or High Temperature Service

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Bars, Forgings and Forging

Chemical Composition			Heat Treatment	
Carbon	C %	0.100 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Chromium	Cr %	18.000 - 21.000		
Sulphur	S %	0.015 max.		
Aluminium	Al %	0.500 - 1.800		
Iron	Fe %	3.000 max.		
Titanium	Ti %	1.800 - 2.700		
Nickel	Ni %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	930 min.
-	-	-	Yield Strength in Mpa	620 min.
-	-	-	Elongation in %	20 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
Nimonic Alloy 80A	Gravity	India	Pipe, Tube, Sheet, Strip, Plate, Hexagon and Wire
B 637 N07080	ASTM	USA	Bars, Forgings and Forging
N07080	UNS	USA	Bars, Forgings and Forging
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com