

Material: ASTM A 1040 1030

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel

Group: Ferrous Mild Steel Alloys

Sub Group: ASTM A 1040 1030 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel

Chemical Composition		
Carbon	C %	0.280 - 0.340
Manganese	Mn %	0.600 - 0.900
Phosphorus	P %	0.030 max.
Sulphur	S %	0.035 max.
Boron	B %	0.0005 - 0.003
Copper	Cu %	0.200 max.
Silicon	Si %	0.100 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As Raw or Annealing or Normalizing or Hardening and Tempering

Mechanical Properties	
Tensile Strength in Mpa	415 - 896
Yield Strength in Mpa	260 min.
Elongation in %	5 min.
Reduction of Area in %	35 - 42
Hardness in HB	137 - 149
Impact in Joule	36.9 - 52.3 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G10300	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1030	SAE	USA	Steel
1030	AISI	USA	Tubing
A 108 Grade 1030	ASTM	USA	Steel and Bar
A 29 1030	ASTM	USA	Steel and Bar
A 510 1030	ASTM	USA	Wire Rod and Round Wire
A 512 Grade 1030	ASTM	USA	Tubing

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India