

Material: ASTM A 1040 1090

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled Steel

Group: Ferrous Mild Steel Alloys

Sub Group: ASTM A 1040 1090 Carbon Steel Compositions For Forging To Hot-Rolled Steel

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel

Chemical Composition		
Carbon	C %	0.850 - 0.980
Manganese	Mn %	0.600 - 0.900
Phosphorus	P %	0.030 max.
Sulphur	S %	0.035 max.
Silicon	Si %	0.100 max.
Boron	B %	0.0005 - 0.003
Copper	Cu %	0.200 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As Raw or Annealing or Normalizing or Hardening and Tempering

Mechanical Properties	
Tensile Strength in Mpa	700 - 840
Yield Strength in Mpa	460 min.
Elongation in %	10 min.
Reduction of Area in %	25 - 40
Hardness in HB	197 - 248
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G10900	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1090	SAE	USA	Steel and Wire
1090	AISI	USA	Steel and Wire
A 29 1090	ASTM	USA	Steel and Bar
A 510 1090	ASTM	USA	Wire Rod, Round Wire and Steel
A 576 10L90	ASTM	USA	Steel and Bar
A 713 G10900	ASTM	USA	Steel and Wire

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India