

## Material: ASTM A 167 S34565

### Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Pressure Vessels and for General Applications

**Group:** Ferrous Stainless Steel Alloys

**Sub Group:** ASTM A 167 S34565 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries

**Grade Belongs to the Industry:** Steel, Sheet, Plate and Strip

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.	Solution Annealing	
Silicon	Si %	1.000 max.		
Manganese	Mn %	5.000 - 7.000		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.010 max.		
Chromium	Cr %	23.000 - 25.000		
Molybdenum	Mo %	4.000 - 5.000		
Nickel	Ni %	16.000 - 18.000		
Niobium	Nb %	0.100 max.		
Nitrogen	N %	0.400 - 0.600		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Tensile Strength in Mpa	793 min.
			Yield Strength in Mpa	414 min.
			Elongation in %	35 min.
			Reduction of Area in %	-
			Hardness in HB	241 max.
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A240 UNS S34565	ASTM	USA	Steel, Plate, Sheet and Strip
S34565	UNS	USA	Steel
A213 S34565	ASTM	USA	Steel and Tube
A249 S34565	ASTM	USA	Steel and Tube
A276 S34565	ASTM	USA	Steel, Bar and Shapes
A312 S34565	ASTM	USA	Steel and Pipe
A959 S34565	ASTM	USA	Steel

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)