

Material: ASTM A 268 TPXM-33

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet and Strip for Pressure Vessels and for General Applications

Group: Ferrous Stainless Steel Alloys

Sub Group: ASTM A 268 TPXM-33 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel and Tube

Chemical Composition		
Carbon	C %	0.060 max.
Silicon	Si %	0.750 max.
Manganese	Mn %	0.750 max.
Phosphorus	P %	0.040 max.
Sulphur	S %	0.020 max.
Chromium	Cr %	25.000 - 27.000
Molybdenum	Mo %	0.750 - 1.500
Nickel	Ni %	0.500 max.
Nitrogen	N %	0.040 max.
Copper	Cu %	0.200 max.
Titanium	Ti %	0.200 - 1.000
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-

Heat Treatment	
	Annealing or Hardening + Tempering

Mechanical Properties	
Tensile Strength in Mpa	470 min.
Yield Strength in Mpa	310 min.
Elongation in %	11 min.
Reduction of Area in %	-
Hardness in HB	241 max.
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A240 UNS S44626	ASTM	USA	Steel, Plate, Sheet and Strip
S44626	UNS	USA	Steel
XM-33	SAE	USA	Steel
A176 Type XM-33	ASTM	USA	Steel, Sheet, Plate and Strip
A959 Type XM-33	ASTM	USA	Steel
A731 Grade TP XM-33	ASTM	USA	Steel and Pipe
A791 Grade TP XM-33	ASTM	USA	Steel and Tube

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India