

Material: ASTM A 269 N08904

Standard Specification for Seamless Ferritic and Austenitic Alloy-Steel Boiler, Superheater, and Heat-Exchanger Tubes

Group: Non-Ferrous Nickel Alloys

Sub Group: ASTM A 269 N08904 Seamless Ferritic and Austenitic Alloy-Steel Boiler, Superheater, and Heat-Exchanger Tubes

Application: Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry: Tube

Chemical Composition		
Carbon	C %	0.020 max.
Silicon	Si %	1.000 max.
Manganese	Mn %	2.000 max.
Chromium	Cr %	19.000 - 23.000
Sulphur	S %	0.030 max.
Molybdenum	Mo %	4.000 - 5.000
Phosphorus	P %	0.040 max.
Copper	Cu %	1.000 - 2.000
Nitrogen	N %	0.100 max.
Nickel	Ni %	23.000 - 28.000
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Cast or Annealing or Age Hardening

Mechanical Properties	
Tensile Strength in Mpa	-
Yield Strength in Mpa	-
Elongation in %	-
Reduction of Area in %	-
Hardness in HRC	90 max.
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 649 N08904	ASTM	USA	Bar and Wire
A 182 F 904L	ASTM	USA	Pipe Flanges, Forged Fittings and Valves
A 213 N08904	ASTM	USA	Tube
A 249 N08904	ASTM	USA	Tube
A 312 N08904	ASTM	USA	Pipe
A 511 N08904	ASTM	USA	Bar
A 965 N08904	ASTM	USA	Forging

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India