

Material: ASTM A 276 XM-29

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet and Strip for Pressure Vessels and for General Applications

Group: Ferrous Stainless Steel Alloys

Sub Group: ASTM A 276 XM-29 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel, Bar and Shapes

Chemical Composition		
Carbon	C %	0.080 max.
Silicon	Si %	1.000 max.
Manganese	Mn %	11.500 - 14.500
Phosphorus	P %	0.060 max.
Sulphur	S %	0.030 max.
Chromium	Cr %	17.000 - 19.000
Nickel	Ni %	2.250 - 3.750
Nitrogen	N %	0.200 - 0.400
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment	
	Solution Annealing

Mechanical Properties	
Tensile Strength in Mpa	690 min.
Yield Strength in Mpa	380 min.
Elongation in %	30 min.
Reduction of Area in %	50 min.
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A240 UNS S24000	ASTM	USA	Steel, Plate, Sheet and Strip
S24000	UNS	USA	Steel and Pipe
XM-290	SAE	USA	Steel
A479 XM-29	ASTM	USA	Steel and Bar
A358 xm-29	ASTM	USA	Steel and Pipe
A314 XM-29	ASTM	USA	Steel, Rolling and Forging
A580 Type XM-29	ASTM	USA	Steel and Wire

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India