

Material: ASTM A 29 1017

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Bar

Group: Ferrous Mild Steel Alloys

Sub Group: ASTM A 29 1017 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Bar

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel and Bar

Chemical Composition		
Carbon	C %	0.150 - 0.200
Manganese	Mn %	0.300 - 0.600
Phosphorus	P %	0.040 Max.
Sulphur	S %	0.050 max.
Copper	Cu %	0.200 max.
Boron	B %	0.0005 - 0.003
Silicon	Si %	0.100 max.
Aluminium	Al %	0.020 max.
Niobium	Nb %	0.025 max.
Vanadium	V %	0.050 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As Raw or Annealing or Normalizing or Hardening and Tempering

Mechanical Properties	
Tensile Strength in Mpa	370 - 410
Yield Strength in Mpa	200 min.
Elongation in %	18 min.
Reduction of Area in %	40 - 50
Hardness in HB	105 - 116
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G10170	UNS	USA	Bars, Wire Rods and Tubing
1017	SAE	USA	Steel and Bar
1017	AISI	USA	Tubing
A 1040 1017	ASTM	USA	Steel
A 29 M1017	ASTM	USA	Steel and Bar
A 510 1017	ASTM	USA	Wire Rod and Round Wire
A 513 Grade 1017	ASTM	USA	Tubing

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India